



TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

TARALAC POLYURATHANE PRIMER

TYPE	Based on Polyurethane Resin & High Quality Anticorrosive Pigments.
FEATURES	Two-pack system, Base & Hardener Packed & supplied separately to mix just before use. This Primer has excellent resistance to corrosion, chemicals, impact and excellent adhesion on priority prepared surfaces. It has good leveling & durability. Can be forced dry/stoving.
RECOMMENDED USE	Top Quality Primer for Auto finishing to be used in Polyurethane Coating System.
PRODUCT DATA	
COLOURS	Off White/Grey
SPECIFIC GRAVITY	1.35 ± 3%
VISCOSITY	90 ± 10 Seconds by Flow Cup No.4 at 30°C
FINISH	Smooth, Uniform, free from Sagging & Wrinkling
GLOSSY	Egg Shell/Matt
DRYING	Surface Dry: 15 Minutes max Track Free: 1 Hour max. Recoating : After Overnight. Full Curing: 7 Days.
FLASH POINT	Above 20°C
APPLICATION DATA	
APPLICATON	By Spray at 25-30 seconds viscosity
THINNER	PU Thinner
MIXING RATIO (BY VOLUME)	Base : Hardener (4:1)
POT LIFE (OF MIXTURE)	1 - 2 Hours
MATURATION TIME	20 to 30 Minutes
STOVING SCHEDULE	70° C for 15 Minutes after 10 Minutes flash off for fast curing & tack free handling

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

TDS Ver.No.: 0216.01/03102016



TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

PERFORMANCE DATA (after Full cure as a system)	
ADHESION	Excellent on properly prepared surfaces.
FLEXIBILITY	Passes ¼" Mandrel
THEORETICAL SPREADING RATE	10-12 Sq.M/Ltr. Per coat at 25-30 µ D.F.T.
CHEMICAL RESISTANCE	
SHELF LIFE	6 months in sealed containers separately packed at normal ambient temperature.
PACKING	4 Ltrs. And 1 Ltrs.

