



TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

TARALAC FAST DRYING AUTO FINISH CLEAR

Taralac Fast Drying Auto finish is prepared form high quality synthetic resin & is formulated to dry quickly & high gloss.

TECHNICAL DATA

Areas of application	Metals
Thinner recommended	Taralac Stov Thinner ST – 1, 555, 111
Method of application	Spraying or Roller
Drying time	Surface dry - 10 minutes Tack Free - 1 Hour 30 minutes Recoating Time – 16-20 hours Full Cure - 48 hours
Finish	Smooth and Glossy
Specific Gravity	0.98 - 1.15 ± 3% (depending on shade)
Viscosity	90 ± 10 Sec by ford cup No.4 at 30C
Covering capacity (spreading by brushing on smooth non absorbent surface)	1000 - 1025 sq. ft./ltr/coat upon the nature of substrate at 5 - 7 microns film thickness
Flash Point	Above 30 ⁰ C (86 ⁰ F)
Gloss	Glossy - > 85%, Matt - <35%
Scratch Hardness	1200 gms
Shade Available	As per Shade Card
Flexibility	No Cracking or Peeling on 1/8” mandrel
Packing Available	20 ltrs., 4 ltrs.

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

TDS Ver.No.: 1301.01/03102016