



TARALAC®

TARA PAINTS & CHEMICALS

A/423/14, Mahagujarat Industrial Estate, Sarkhej-Bavla Road, B/h. Sarvottam Hotel Lane, Village-Moraiya, Ahmedabad - 382210

Tel: (F): +918000011774

E-mail: taralac@hotmail.com

Web: www.taralac.com

EPOXY PAINT & CLEAR

General Description:

TARALAC EPOXY is a solvent based, two-component epoxy system containing of an epoxy resin and polyamide hardener.

Major Uses:

TARALAC EPOXY is specially formulated to give excellent coating for steel structures, concrete and ideal for application for commercial, industrial and chemical plants.

Advantages:

- Chemical and abrasion resistant.
- Flexible and waterproof.
- Gives corrosion resistant to steel.
- Non – toxic when fully cured.
- Available in long range of colours.

Characteristics and Physical Properties:

Colour	Any choice of colour.			
Mixing Ratio	3: 1			
Volume Solids	59%			
Pot Life	10°C (50°F) 12 hours	15°C (59°F) 10 hours	25°C (77°F) 3 hours	40°C (104°F) 2 hours
Dry film thickness	50 microns.			
Flash Point	22°C.			

Drying Time:

To Recoat	3 – 5 hrs.
To Hard dry	12 hrs – 16 hrs.
Fully Cured	5 Days.
Shelf Life	1 year.
Coverage	10 – 12m ² / lit.

Mixing and Application:

Mix component A and B at specified ratio ensuring they are complete homogenous. After thoroughly mix, allow the mixture to stand for 15 – 20 minutes. Apply either by brush, roller or airless spray gun. Method of Application: By brush, roller airless and Conventional Spray

Spray Data

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information.

TDS Ver.: 2600.01/25052015



TARALAC®

TARA PAINTS & CHEMICALS

A/423/14, Mahagujarat Industrial Estate, Sarkhej-Bavla Road, B/h. Sarvottam Hotel Lane, Village-Moraiya, Ahmedabad - 382210

Tel: (F): +918000011774

E-mail: taralac@hotmail.com

Web: www.taralac.com

Conventional Spray

Nozzle Orifice	2 – 3mm.
Nozzle Pressure	43 – 57 psi
Dilution	5 – 10 %
Thinner	Taralac Epoxy Thinner

Airless Spray

Nozzle Orifice	0.38 – 0.46 mm
Nozzle Pressure	1138 - 1710 psi
Dilution	10 - 15%
Thinner	Taralac Epoxy Thinner

Typical Recommended System:

Steel

BASECOAT	2 COATS
TOPCOAT	1 COAT.

Concrete

EPOXY SEALER	1 COATS
TOPCOAT	2 COATS

Chemical Resistance:

Salt Spray test 1000 hrs	- Passes as per IS 101
Hydrochloric Acid	- Very Good.
Nitric Acid, 10%	- Good.
Acetic Acid, 5%	- Good.
Sulphuric Acid, 20%	- Good.
Phosphoric Acid, 20%	- Good.
Lactic Acid, 20%	- Good.
Sodium hydroxide, 50%	- Very Good.
Petrol	- Very Good.
Alcohol	- Very Good.
Ketones	- Good.

Heat Resistance & Sunlight Exposure:

Some special grades of Epoxy are stable upto 250C. Except for pigments which may change shade. Epoxies are sensitive to Sunlight & should not be applied in the fully exposed condition. Excessive exposure to sunlight may result in chalking or colour change.

Surface Preparation:

Steel:

Surface must be clean, dry and free from dust, oil, grease and some foreign matters. Recommended methods for repairing steel are by Sa 2 ½ sandblasting, wire brushing and derusting.

Concrete:

Allow new concrete to cure for 28 days, and surface should be sound and no strange particles prior to application. Ensure that the surface to be coated is properly etched and washed before the application of Taralac Epoxy

Priming:

- Steel surface should be primed with Taralac Epoxy HB Primers Basecoat prior to applications of top Coat.
- Concrete should be primed with 1 coat of Primer Sealer as a concrete conditioner prior to the application of Top Coat.



TARALAC®

TARA PAINTS & CHEMICALS

A/423/14, Mahagujarat Industrial Estate, Sarkhej-Bavla Road, B/h. Sarvottam Hotel Lane, Village-Moraiya, Ahmedabad - 382210

Tel: (F): +918000011774

E-mail: taralac@hotmail.com

Web: www.taralac.com

Storage:

Keep resin and hardener in a cool place below 25°C. Keep the container tightly closed. Shelf life of 12 months minimum.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or Epoxy Thinner as soon as possible.

Physiological Hazards:

Keep Resin and Hardener away from eyes and skin contact. Good ventilation should be provided particularly in closed work areas. Keep uncured epoxy materials away from the mouth, food or drink, do not use empty tins to store food and do not empty cans into drains. Always wear gloves and safety materials when handling this product. Clean any splashes or smears from the skin immediately, using warm water and soap. Avoid inhaling vapor.