



TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

TDS AD ALKYD PHENOLIC GOLD VARNISH

Alkyd Phenolic based fast curing very good flexibility, high bonding strength, good surface built up, good insulating properties, Impregnation of fan stators, Impregnation of Motors, Generators & Transformers, short curing schedule & serves as a good protection against moisture, fungus, corrosion, dust, etc.

Technical Data

Chemical base	Phenolic
Viscosity by Flow Cup 4 (s)	23 – 35
Curing Time	24 hr at RT
Thinner Recommended	Thinner ST – 2
Thermal Class	130 (B)
Electrical Strength at 25C kV/mm as per IS	40
Flash Point	Above 30 C
Packing Available	1lt, 4lt, 20lt