

## 0215-0216 1K Pu Primer

TYPE	Based on Polyurethane Resin & High Quality Anticorrosive Pigments.
FEATURES	This Primer has excellent resistance to corrosion, chemicals, impact and excellent adhesion on priority prepared surfaces. It has good levelling & durability. Can be forced dry/stoving.
RECOMMENDED USE	Top Quality Primer for Auto finishing to be used in Polyurethane Coating System.
<b>PRODUCT DATA</b>	
COLOURS	Off White/Grey
SPECIFIC GRAVITY	1.35 $\pm$ 3%
VISCOSITY	90 $\pm$ 10 Seconds by Flow Cup No.4 at 30°C
FINISH	Smooth, Uniform, free from Sagging & Wrinkling
GLOSSY	Egg Shell/Matt
DRYING	Surface Dry: 15 Minutes max Track Free: 1 Hour max. Recoating: After Overnight. Full Curing: 7 Days.
FLASH POINT	Above 20°C
<b>APPLICATION DATA</b>	
APPLICATION	By Spray at 25-30 seconds viscosity
THINNER	PU Thinner
MATURATION TIME	20 to 30 Minutes
STOVING SCHEDULE	70° C for 15 Minutes after 10 Minutes flash off for fast curing & tack free handling
<b>PERFORMANCE DATA (after Full cure as a system)</b>	
ADHESION	Excellent on properly prepared surfaces.
FLEXIBILITY	Passes 1/4" Mandrel
THEORETICAL SPREADING RATE	8-10 Sq.M/Ltr. Per coat at 25-30 $\mu$ D.F.T.
<b>CHEMICAL RESISTANCE</b>	
SHELF LIFE	6 months in sealed containers separately packed at normal ambient temperature.
PACKING	4 Ltr. And 1 Ltr.



# TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,  
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: [taralac@hotmail.com](mailto:taralac@hotmail.com) , [taralac@taralac.com](mailto:taralac@taralac.com) Website: [www.taralac.com](http://www.taralac.com)

## Mention below the 1k Pu Primer Shades:-

0215 1K Pu Primer Grey
0216 1K Pu Primer White

