

## 0217 Syn Wood Primer White

TARALAC WOOD PRIMER WHITE is a high solid alkyd primer. High-quality alkyd resin based primer for the properly cleaned Wood surface. Contains extremely high solids content. It is not intended for use on the inside of potable water tanks or for marine environmental use.

### TECHNICAL DATA

Areas of application	Wood
Thinner recommended	Taralac St Thinner ST – 2
Method of application	Brushing or Spraying
Drying time	Surface dry - less than 30 minutes. Hard dry - less than 18 hours
Fineness of Grind	5 Hegman Minimum
Finish	Smooth and Matt
Covering capacity (spreading by brushing on smooth non-absorbent surface)	15 - 18 sq. Mts./ltr/coat depending upon the nature of the substrate at 20 - 25 microns film thickness
Flash Point	Above 30° C (86° F)
Packing Available	20 ltr., 4 ltr., 1 ltr., 500 ml., 200 ml.,
Gloss (60°)	2 – 6%

### SURFACE PREPARATION:

The surface must be clean, dry and free of all contamination before application of primer. Non-ferrous metals must be primed with metal pre-treatment wash primer. The surface must be cleaned and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

### Directions for use:

Ensure that the surface to be painted is free from loose matter, dust etc. Apply a coat of paint by brushing after adjusting consistency using the recommended thinner. It can also be applied by spray applications.

### ADVANTAGES:

- (1). Low V.O.C. (Volatile Organic Compound) Content
- (2). Excellent Corrosion Resistance
- (3). Fast Drying

### PRECAUTIONS:

CONTENTS ARE FLAMMABLE! KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. USE WITH ADEQUATE VENTILATION. AVOID BREATHING VAPORS OR MIST!  
AVOID CONTACT WITH SKIN AND EYES. DO NOT USE IN-TANK OR PIT WITHOUT PROPER PROTECTION! READ MATERIAL SAFETY DATA SHEET BEFORE USING.